

# UTAH DEPARTMENT OF TRANSPORTATION

## TECHNICAL BULLETIN MT

September 12, 2018

### ASPHALT SURFACING MATERIALS- TYPICAL APPLICATION RATES

A designer should have a basic knowledge of how the various paving materials are placed in construction so they can correctly determine the correct paving quantities.



The information provided herein is approximate and for estimating purposes only; typical values have been assumed and any values may change considerably for a specific location. You should verify the unit weights with the Region Materials Engineer.

#### Surface Treatments

1. Open-Graded Surface Course  
Weight: 135 lb/ft<sup>3</sup>  
Asphalt: PG Binder, 6.25%
2. Chip Seal Coat  
Emulsion: CRS-2, CRS-2P, LMCRS-2, HFMS-2, HFMS-2P  
0.35 gal/yd<sup>2</sup> (New Pavement)  
0.45 gal/yd<sup>2</sup> (Milled Pavement)
3. Prime Coat  
Cut-Back: MC-70 or MC-250  
0.5 gal/yd<sup>2</sup>
4. Tack Coat  
Emulsion: CSS-1, CSS-1H, SS-1, SS-1H (diluted 2 parts emulsion to 1 part water)  
0.10 gal/yd<sup>2</sup> (New Pavement)  
0.15 gal/yd<sup>2</sup> (Milled Pavement)
5. Flush Coat  
Emulsion: CSS-1, CSS-1H, SS-1, SS-1H, HFMS-2P (diluted 2 parts emulsion to 1 part water)  
0.12 gal/yd<sup>2</sup>

---

## **B. Surface Courses**

### 1. Hot Mix Asphalt

Weight: 152 lb/ft<sup>3</sup>

Asphalt: 5.20% of total wet weight

## **C. Base Courses**

### 1. Lean Concrete Base: bid by square yard, @ 4 inch thick

### 2. Untreated Base Course

Weight: 138 lb/ft<sup>3</sup>

### 3. Granular Borrow

Weight: 133 lb/ft<sup>3</sup>

## **FURTHER INFORMATION**

UDOT Standard Specification 02745, Asphalt Materials

Asphalt Institute Manual Series No. 19, "A Basic Emulsion Manual"

Asphalt Institute Manual Series No. 4, "The Asphalt Handbook"

## **UDOT CONTACTS**

Scott Andrus, Engineer for Materials, (801) 965-4859, [scottandrus@utah.gov](mailto:scottandrus@utah.gov)

Howard Anderson, State Asphalt Engineer, (801) 965-4296, [handerson@utah.gov](mailto:handerson@utah.gov)

Curt Mcquiston, Region One Materials Engineer, (801) 889-6607, [cmccuiston@utah.gov](mailto:cmccuiston@utah.gov)

Lonnie Marchant, Region Two Materials Engineer, (801) 975-4926, [lmarchant@utah.gov](mailto:lmarchant@utah.gov)

Steve Park, Region Three Materials Engineer, (801) 227-8035, [stevepark@utah.gov](mailto:stevepark@utah.gov)

Cameron Gay, Region Four Materials Engineer, (435) 893-4742, [cameron@utah.gov](mailto:cameron@utah.gov)